


Technical Product Information

Mercer Stendal TCF (typical properties)

Northern Bleached Softwood Kraftpulp made of pine (40 to 70 %) and spruce (30 to 60 %) PFI-mill at 23°C and 50 % relative humidity



Beating revolutions		0	1000	2000	5000	9000	11000	CoV [%] 5000 rev	Method
Density	kg/m ³	559	647	693	752	792	808	1.2	DIN EN ISO 534
Drainage resistance*	SR	12	14	15	22	41	52	5.2	DIN EN ISO 5267-1
Tensile index	kNm/kg	23.4	55.7	72.0	92.2	102	103	3.3	DIN ISO 1924-3
Elongation	%	2.4	3.6	3.9	3.8	3.7	3.6	3.1	DIN ISO 1924-3
Tear Index	Nm ² /kg	17.3	21.5	17.1	13.0	11.6	11.2	5.7	DIN EN ISO 1974
Burst Index	MN/kg	1.5	4.0	5.3	6.8	7.3	7.3	5.7	DIN EN ISO 2758
Gurley air permeability	s / 100 ml	1.3	3.5	6.2	23.6	126	232	21	ISO 5636-5
Light scattering coefficient	m ² /kg	31.9	25.6	22.7	19.5	17.4	17.0	2.6	ISO 9416
Opacity	%	76.7	72.3	70.0	66.1	63.4	62.8	0.8	ISO 2471

*Analysed using tap water Sheet former (Rapid Köthen)


General Properties	Typical values	Target value	Unit	Method SCAN	Fibre dimensions	Typical values	CoV	Unit	Equipment
ISO Brightness	86.0	>84.5	% ISO	ISO 3688					
Sheet brightness	85.2	-	%	ISO 2470	Fibre length	2.17	1.4	mm	Pulp Eye
Brightness reversion	4.3	-	%	ISO 5630-1*	Fibre width	28.6	0.6	µm	Pulp Eye
Dirt count	1.3	<3	mm ² /kg	DIN EN ISO 5350-2					
Intrinsic Viscosity	727	>600	ml / g	ISO 5351					
Extractives	0.06	<0.10	%	SCAN CM 49:03					
Ash	0.23	<0.30	%	ISO 1762					
pH	5.0	-		SCAN P 14:65**					
Organic chlorine in pulp	8.6	<30	mg/kg	SCAN CM 52:94					
AOX removable by washing	0.6	<5	mg/kg	SCAN CM 44:97					

* time 24 h ** use of KCl instead of deion. water



Bale marking

- 1 – Mill and pulp grade (ECF, TCF, other/XXXX)
- 2 – Mill (Mercer Rosenthal: 2, Mercer Stendal: 3)
- 3 – Year (18 for 2018)
- 4 – Charge number
- 5 – Unit number
- 6 – Production time (Stendal only)



Dimensions Standard bales



Standard bales

Bales: 85 x 80 x 40 cm (l x w x h)
 250 kg
 3 wires (one alongside, two cross)

Stack: 4 bales

Unit: 2 stacks resp. 8 bales
 2 tons
 8 wires
 160 x 85 x 160 cm (l x w x h)

Wire Material: Zinc plated steel



Dimensions Jumbo/Big bales (Stendal only)

Bales: 85 x 80 x 160 (l x w x h)
 1 ton
 2 wires (cross)

Unit: 2 stacks resp. 2 bales
 2 tons
 8 wires
 160 x 85 x 160 cm (l x w x h)

Wire Material: Zinc plated steel